

TECHNICAL DATA SHEET

SUNBRELLA® AWNING / MARINE 152

Fiber Content 100 % Solution Dyed Acrylic

Test Name	Test Method	Basis	Nominal Value
Fabric Construction: Ends	ASTM D3775-98	Each	76
Fabric Construction: Picks	ASTM D3775-98	Each	36
Fabric Weight	ASTM D3776-96	Grams / Square Meter	350
Finished Fabric Width	ASTM D3774-96	cm	152
Hydrostatic Test	AATCC 127-1998	cm	40
Oil Repellency	AATCC 118-1997	Grade	5
Spray (Large)	AATCC 22-2001 (Modified)	Rating	100 Front 100 back
Break Strength	ASTM D5034-95	Kg. of force	129.2 Warp 81.6 Filling
Tear strength	ASTM D2261-96	Kg. of force	5.4 Warp 3.6 Filling
Tabor Stiffness	ASTM D1388-96	Tabor Unit	10.0
Wyzenbeek Abrasion-Wire Screen	ASTM D4157-92	Cycle	40,000 Warp 40,000 Filling
California Technical Bulletin #117 (Flammability)	TB 117	Pass / Fail	CS191-53 Class 1 Pass
Colourfastness to light	SA 1960J	Grade	Grade 4 @ 1500 hrs.

Glen Raven® Revision Date: 03/06/18 – Sunbrella awning – Marine 60 (AND-QA-TD-001)